



PTT 系列複合材料物性表

compound datasheets

項目 Property		試驗法 ASTM Method	單位 Units	PTT, GF10	PTT, GF20	PTT, GF30	PTT, GF40	PTT FR, GF30	PTT, CF10	PTT CF20	PTT CF30	
一般性質	比重 Specific Gravity	D792	-	1.41	1.49	1.57	1.65	1.7	1.37	1.39	1.43	
	成型收縮率 Mold Shrinkage	6.35mm截面	D955	%	-	-	-	-	-	-	-	
		3.18mm截面			0.4~0.8	0.2~0.5	0.1~0.3	0.1~0.3	0.15~0.3	0.1~0.3	0.05~0.15	<0.1
吸水率(24 hours) Water absorption, 24 hrs @ 23°C	D570	%	-	-	-	-	-	-	-	-	-	
機械性質	衝擊強度 Impact Strength	3.18mm截面(缺口) Notched Izod	D256	J/m	32	43	53	80	64	37	43	43
		3.18mm截面(無缺口) Unnotched Izod			267	320	481	641	427	374	427	481
	伸張強度 Tensile Strength	D638	MPa	76	107	117	138	124	131	159	165	
	延伸率 Tensile Elongation	D638	%	3~4	2~3	1.5~2.5	1~2	1~2	1~2	1~2	1~2	
	伸張模數 Tensile Modulus	D638	MPa	3103	6895	8964	13100	12066	10342	15169	21374	
	彈性強度 Flexural Strength	D790	MPa	117	152	165	193	172	186	221	234	
	彈性模數 Flexural Modulus	D790	MPa	4137	6206	8274	12411	11377	9653	13790	18616	
洛氏硬度 Rockwell Hardness	D785	-	-	-	-	-	-	-	-	-	-	
熱性質	熱變形溫度 DTUL	at 264 psi (1.82 MPa)	D648	°C	-	-	207	-	210	-	-	
		at 66 psi (0.455 MPa)			-	-	-	-	-	-	-	-
	連續使用溫度 Continuous Use Temp.	UL-746B	°C	-	-	-	-	-	-	-	-	
	線性熱膨脹係數 Coefficient of Linear Thermal Expansion	D 696	10 ⁻⁵ /°C	-	-	-	-	-	-	-	-	
防火等級 Flammability thickness	-	-	-	*HB @ 1.5 mm	*HB @ 1.5 mm	*HB @ 1.5 mm	*HB @ 1.5 mm	V-0 @ 0.8 mm	*HB @ 1.5 mm	*HB @ 1.5 mm	*HB @ 1.5 mm	
電氣性質	體積固有電阻 Volume Resistivity	D257	ohm-cm	-	-	-	-	-	-	-	-	
	表面電阻 Surface Resistivity	D257	ohm/SQ	-	-	-	-	-	-	-	-	
	靜電消散(MIL-PRF-81705C) Static Decay	FTMS-4046.1	sec	-	-	-	-	-	-	-	-	

*Tested by factory.

Data are obtained from specimens molded under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.